

2-(Morpholiniothio)-benzothiazole**TECHNICAL DATA SHEET**

Emerald Performance Materials offers a range of delayed-action sulfenamide accelerators under the Cure-Rite® brand name. Sulfenamides affect both vulcanization parameters (scorch delay, cure rate, etc), as well as physical properties of the vulcanizate (modulus, elasticity, cross-link density, etc). Cure-Rite® sulfenamides are offered in several forms, including pellets powder, and flake. Pellets confer low dust, high actives, low friability and good dispersion properties. Cure-Rite® sulfenamides are most effective if stored in cool (<30° C), dry conditions (<60% RH) and if used within 6 months of date of manufacture.

Specific properties for Cure-Rite® OBTS are listed below.

PRODUCT DESCRIPTION

- Tan to yellow flakes

FEATURES

- Better scorch safety
- Fast cure rate
- Medium cross-link density
- Non-staining & non-blooming

BENEFITS

- Vulcanizates have dynamic elasticity
- Excellent with fine carbon blacks
- Longer delayed vulcanization affords good flow for intricate parts

APPLICATIONS

- Tire treads, sidewall and carcass
- Molded & injected rubber goods
- Footwear

TYPICAL PROPERTIES

Melting Point	80-87°C
Ash	<0.15%
Methanol Insolubles	<0.5%
Free Amine	<0.3%
Moisture	<0.2%

STORAGE/HANDLING

Optimal product performance is attained, if OBTS is used within 3 months from manufacturing date. OBTS should be stored in a location that is cool and dry. Read the OBTS Material Safety Data Sheet before handling, storing, or using.

PACKAGING/DELIVERY

Available in paper bags

To obtain samples, discuss your application, or gather more details on Cure-Rite® OBTS, or any other Cure-Rite® product, please log onto our website at www.emeraldmaterials.com, or contact us directly at 888.889.9150.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in process these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Emerald Performance Materials shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Emerald's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered permission, recommendation, not as an inducement to practice any patented invention without permission of the patent owner. IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.